



0070110A7

110 Delta Drive
 Pittsburgh, PA 15238
 NAFTA Sales: (1)800-245-3984
 HK Sales : (852)3102-9337
 magnetics@spang.com



| Kool M μ Ultra Permeability (μ) | A _L (nH/T ²) | Core Marking | | | Coating Color |
|---|-------------------------------------|--------------|-------------|------------------|---------------|
| | | Lot Number | Part Number | Inductance Grade | |
| 60 | 76 \pm 8% | XXXXXX | 70110A7 | N/A | Black |

| Dimensions | Uncoated | | Coated Limits | | | Packaging |
|------------|----------|-------|---------------|-------|-----|---------------------------------------|
| | (mm) | (in) | (mm) | (in) | | |
| OD (A) | 57.15 | 2.250 | 58.04 | 2.285 | max | Cardboard cut-outs Box Qty= 90 pcs |
| ID (B) | 35.56 | 1.400 | 34.75 | 1.368 | min | |
| HT (C) | 13.97 | 0.550 | 14.86 | 0.585 | max | |

| Electrical Characteristics | | | Physical Characteristics | | | | | | |
|---|------------------------|-----|---|-------------------------|---|---|---------------------------------|--|-----------------|
| Watt Loss @ 100kHz, 100mT max (mW/cm ³) | DC Bias min (oersteds) | | Voltage Breakdown wire to wire min (V _{AC}) | Break Strength min (kg) | Window Area W _a (mm ²) | Cross Section A _e (mm ²) | Path Length L _e (mm) | Volume V _e (mm ³) | Est. Weight (g) |
| | 80% | 50% | | | | | | | |
| 250 | 45 | 100 | 3000 | 107.0 | 948 | 144 | 143 | 20,700 | 128 |

| Winding Information | | | | | Temperature Rating | |
|-------------------------|------|----------------|------|---------------------------------|--------------------|--|
| Winding Length Per Turn | | | | Wound Coil Dimensions (mm) | | Curie Temp: 500°C |
| Winding Factor | (mm) | Winding Factor | (mm) | 40% Winding Factor | | Coating Temp (Continuous up to): 200°C |
| | | | | OD | 65.2 | Notes: |
| 0% | 53.0 | 40% | 70.8 | HT | 25.7 | |
| | | | | Completely Full Window | | |
| 20% | 62.0 | 45% | 73.5 | Max HT | 40.1 | |
| 25% | 64.2 | 50% | 75.9 | Surface Area (mm ²) | | |
| 30% | 66.0 | 60% | 81.3 | Unwound Core | 7,700 | |
| 35% | 68.8 | 70% | 87.5 | 40% Winding Factor | 13,000 | |

