



0079601A7

110 Delta Drive
 Pittsburgh, PA 15238
 NAFTA Sales: (1)800-245-3984
 HK Sales : (852)3102-9337
 magnetics@spang.com



Kool M μ MAX Permeability (μ)	A _L (nH/T ²)	Core Marking			Coating Color
		Lot Number	Part Number	Inductance Grade	
26	54 \pm 8%	XXXXXX	79601A7	N/A	Black

Dimensions	Uncoated		Coated Limits			Packaging
	(mm)	(in)	(mm)	(in)		
OD (A)	59.60	2.346	60.60	2.385	max	Cardboard cut-outs Box Qty= 63 pcs
ID (B)	34.00	1.338	33.00	1.299	min	
HT (C)	19.50	0.767	20.50	0.807	max	

Electrical Characteristics			Physical Characteristics						
Watt Loss @ 100kHz, 100mT max (mW/cm ³)	DC Bias min (oersteds)		Voltage Breakdown wire to wire min (V _{AC})	Break Strength min (kg)	Window Area W _a (mm ²)	Cross Section A _e (mm ²)	Path Length L _e (mm)	Volume V _e (mm ³)	Est. Weight (g)
	700	80%							
	135	285							

Winding Information					Temperature Rating		
Winding Length Per Turn				Wound Coil Dimensions (mm)			
Winding Factor	(mm)	Winding Factor	(mm)	40% Winding Factor	OD	67.4	
					HT	30.7	
0%	68.6	40%	85.5	Completely Full Window	Max OD	70.8	
					Max HT	44.3	
20%	77.3	45%	88.2	Surface Area (mm ²)			
25%	79.2	50%	90.5				
30%	81.2	60%	95.8	Unwound Core			10,000
35%	83.6	70%	102	40% Winding Factor			15,000

Curie Temp: 500°C
 Coating Temp (Continuous up to): 200°C
 Notes:

