



Specification for:
0F43615TC

110 Delta Drive
Pittsburgh, PA 15238
Phone: 412/696-1333
Fax: 412/696-0333
Email:magnetics@spang.com

DIMENSIONS



(mm)	Uncoated Nominal:	Min:	Max:
O.D. (A)	36.0	35.30	36.70
I.D. (B)	23.0	22.50	23.50
Ht. (C)	15.0	14.76	15.24

Eff. Parameters		
A _e mm ²	l _e mm	V _e mm ³
95.9	89.6	8596

INDUCTANCE

AL value (nH/T ²)	Test conditions
4040 ± 20%	10 kHz, 0.5 mT (For N = 5, use 1.4 mA), 25°C

CORE LOSSES

P _L max	Production lot limit Max avg	Test conditions
1.84 W (214 mW/cm ³)	1.67 W (194 mW/cm ³)	25 kHz, 200 mT, 100°C
-	-	-

COATING

Uncoated

NOTE

Spec. Modifications	Previous	Revised
2006.01.13	OD max = 36.50 Losses: General F material	OD max = 36.70 Losses: Detail as indicated