




Specification for:

ZJ46113TC

110 Delta Drive
 Pittsburgh, PA 15238
 Phone: 412/696-1333
 Fax: 412/696-0333
 Email:magnetics@spang.com

DIMENSIONS



(mm)	Uncoated Nominal:	Coated Min:	Coated Max:
O.D. (A)	61.0	60.27	62.23
I.D. (B)	35.6	34.29	36.41
Ht. (C)	12.7	12.56	13.34

Eff. Parameters		
A_e mm ²	l_e mm	V_e mm ³
157.4	144.6	22774

INDUCTANCE

A_L value (nH/T ²)	Test conditions	
6845 ± 20%	10 kHz	0.5 mT (For N = 1, use 6.8 mA), 25°C
> 5134	150 kHz	

ELECTRICAL LOSSES

$\tan \delta / \mu_i$	Test conditions
≤ 20 · 10 ⁻⁶	100 kHz, 0.5 mT, 25°C

COATING

Epoxy rated for 200°C continuous operation.
Voltage breakdown rating 2000 V Min Wire-to-Wire.

NOTE

Spec. Modifications	Previous	Revised
2006.01.15	LF: General J Material Breakdown voltage > 1000 V	LF & Freq Response: Detail as indicated Breakdown voltage > 2000 V