




Specification for:
ZP44715TC

110 Delta Drive
Pittsburgh, PA 15238
Phone: 412/696-1333
Fax: 412/696-0333
Email:magnetics@spang.com

DIMENSIONS



(mm)	Uncoated Nominal:	Coated Min:	Coated Max:
O.D. (A)	46.9	46.26	48.04
I.D. (B)	27	25.85	27.65
Ht. (C)	14.8	14.95	15.65

Eff. Parameters		
A _e mm ²	l _e mm	V _e mm ³
143.5	110.4	15848

INDUCTANCE

AL value (nH/T ²)	Test conditions
4030 ± 25%	10kHz, 0.5 mT (For N = 5, use 0.41 mA), 25°C

CORE LOSSES

P _L max	Production lot limit Max avg	Test conditions
1949 mW (123 mW/cm ³)	1775 mW (112 mW/cm ³)	100 kHz, 100 mT, 100°C
-	-	-

COATING

Epoxy rated for 200°C continuous operation.
Voltage breakdown rating 2000 V Min Wire-to-Wire.

NOTE

Spec. Modifications	Previous	Revised
2006.01.12	Bare Nom Ht = 15.0 Losses: General P Material Breakdown voltage > 1,000 V	Bare Nom Ht = 14.8 Losses: Detail as indicated Breakdown voltage > 2,000 V